

CARATTERISTICHE TECNICHE OAK **RAFFAELLO**



1. **Product description:** (Quercus Petrae) Parquet oak RAFFAELLO
2. **Board sizes:** 14 x 155 x 1800
3. **Top layer:** 3,4 mm (nominal)
4. **Finishing:** grading ANTIQUE, handscraped, UV white oiled, white washed, micro-bevel on 4 sides
5. **Incastro:** 



Figura 1,2 Illustrative Photo. The picture shows only the characteristics of grade

Sliperiness	USRV 40 x Oiled	EN 14342 - 2013	
Fire Resistance	Cfl-s1	EN 14342 - 2013	
Formaldehyde Emission	E1	EN 717- 1 : 2004-10	
Thermal Conductivity	0,14 W/(m*K)	EN 14342 - 2013	
Bending Strength	3240N	EN 14342 - 2013	
Content of PCP	<5	CEN/TR 14823:2004	

CARATTERISTICS:

The oak used for the top layer comes from certified German or French forests, the middle–and back layer wood is harvested on Indonesian plantations

Knots are allowed in unlimited size and number. Sound knots have to be 5 mm away from the edge, cracked knots are filled with black putty filler. Cracks and holes, filled with black putty filler, and a width of max. 3 mm and 450 mm length are allowed. Sapwood is allowed Putty filler is allowed on every board. Color variations are allowed. Top layer: Klumpp Coatings UV oil

Suitable for underfloor heating systems – please check the installation manual for further information! For maintenance and care use the CAVINATO “M&C” recommended products, for the validity of the guarantee.