

## CARATTERISTICHE TECNICHE OAK **REMBRANDT**

**Product description:** (Quercus Petrae) Parquet oak REMBRANDT

**Board sizes:** 14 x 180 x 1800


**Top layer:** 3,4 mm (nominal)

**Finishing:** Oak, Masteroil ready to use, brushed

**Incastro:** 



**Figura 1,2** Illustrative Photo. The picture shows only the characteristics of grade

Sliperiness	USRV 40 x Oiled	EN 14342 - 2013	
Fire Resistance	Cfl-s1	EN 14342 - 2013	
Formaldehyde Emission	E1	EN 717- 1 : 2004-10	
Thermal Conductivity	0,14 W/(m*K)	EN 14342 - 2013	
Bending Strength	3240N	EN 14342 - 2013	
Content of PCP	<5	CEN/TR 14823:2004	

### CARATTERISTICS:

The oak used for the top layer comes from certified German or French forests, the middle- and back layer wood is harvested on Indonesian plantations.

Knots are allowed in unlimited size and number.

Sound knots have to be 5 mm away from the edge, cracked knots are filled with brown putty filler. Cracks and holes, filled with brown putty, and a width of 12 mm and unlimited length allowed. Sapwood is allowed. Putty filler is allowed on every board. Color variations are allowed.

Finish: WoCa ready to use oil. A second oiling of the installed flooring is not necessary.

Suitable for underfloor heating systems – please check the installation manual for further information!

For maintenance and care use the CAVINATO “M&C” recommended products, for the validity of the guarantee.